



EXCELON GO-1480[®]

Chemical and Petrochemical Transfer Tubing



Physical Properties**

Hardness, Shore A	62
Tensile Strength, psi	1980
Elongation at Break, %	730
Brittle Temperature, °F	-20.2
Specific Gravity	1.25

** Values listed are typical and are meant only as a guide to aid in design. Field testing should be performed to find the actual values for your application.

GO-1480

ID	OD	STOCK NO.	WALL	LENGTH	LBS./FT.	MAX. WKG. PSI AT 73°F	PART NO.
3/32	5/32	GO1	1/32	50'	0.007	42	45901805
1/8	1/4	GO2	1/16	100'	0.019	68	4502
1/8	1/4	GO2	1/16	50'	0.019	68	450205
3/16	5/16	GO3	1/16	100'	0.028	55	4503
3/16	5/16	GO3	1/16	50'	0.028	55	450305
1/4	3/8	GO6	1/16	100'	0.032	55	4506
1/4	3/8	GO6	1/16	50'	0.032	55	450605
5/16	7/16	GO9	1/16	50'	0.040	50	450905
3/8	1/2	GO12	1/16	100'	0.045	40	4512
3/8	1/2	GO12	1/16	50'	0.045	40	451205
7/16	9/16	GO15	1/16	50'	0.053	40	451505
1/2	5/8	GO18	1/16	50'	0.060	30	451805
1/2	3/4	GO20	1/8	100'	0.128	45	4520
1/2	3/4	GO20	1/8	50'	0.128	45	452005
5/8	7/8	GO26	1/8	50'	0.160	40	452605
3/4	1	GO31	1/8	50'	0.186	35	453105

Special order and custom runs available.
Product samples are available upon request

- For use in the transfer of chemicals and petrochemicals including: gasoline, kerosene, oils and cutting compounds
- Specifically formulated to resist hardening and swelling
- Transparent and flexible
- Protects against leaching and product contamination

GO-1480 is not to be used in contact with food, beverage or drugs.

TPI stocks transparent yellow GO-1480 in the twelve sizes necessary to supply applications involving gas and oil.



TUBE SNIP CUTTER

Part No: 39000

The Excelon Tube Snip Cutter easily makes clean, smooth cuts and works well with GO-1480 tubing.

Also available, Excelon Tube Snip Cutter Replacement Blades (Part No: 38000).



Thermoplastic Processes
A TPI Partners Corporation